

TRANS[®]
PAINT



PLUS INDUSTRIAL FINISH





PLUSS INDUSTRIAL FINISH

Premium steel structure finish (solvent-based)	
Standard Packing	1L & 5L
Colour	As per colour chart
Application	Exterior and Interior
For use on	Iron/steel
• Solvent based high gloss finish • Fast drying • Tough and durable paint film	

PLUSS INDUSTRIAL FINISH

This is high gloss oil-based alkyd finish specially designed to provide a durable and anti-corrosive finish on metal surfaces. It is fast drying and develops to a tough film suitable for use on any industrial structures that require protection from rust and harsh weather elements.

Colour	<i>See Protective & Industrial Coatings Card</i>	
Pack Size	1 and 5 litres	
Composition	<i>Binder</i>	Modified medium-oil alkyd
	<i>Pigment</i>	Organic/Inorganic pigments and mineral extenders
	<i>Solvent</i>	Hydrocarbon mixture
Volume Solid	Average 42 ± 2%, varying with colours	
Recommended Dry Film thickness	35 – 45 microns (per coat)	
Drying Times *	<i>Touch Dry</i>	Within 8 hours
	<i>Hard Dry</i>	Within 16 hours
Full Cure *	3 – 4 weeks; Time for the coating to reach its full chemical/mechanical properties and will resist and perform as per the properties featured	
Over-coating Interval *	Minimum 16 hours	
Spreading Rate *	10 – 13 m ² /litre/coat	
Application	<i>Brush/Roller</i>	Use as is, thin not exceeding 5% by volume with paint thinner or white spirit/mineral turpentine if necessary
	<i>Conventional Spray</i>	Thin with paint thinner or white spirit/mineral turpentine to 20% by volume
	<i>Airless Spray</i>	Use as is
Surface Preparation	<u><i>New Unpainted Surface</i></u>	<u><i>Previous Painted Surface</i></u>
<i>Metal/Mild Steel</i>	- Remove rust or mill scales by manual or mechanical cleaning - Ensure surface free from oil, grease and other contaminant	- Remove loose adhering paint - Remove debris, oil, grease or other contaminant before painting
Recommended Painting System	<u><i>Sequence</i></u>	<u><i>Product</i></u>
<i>Metal/Mild Steel</i>	Primer (1 coat) Finish (2 coats)	PLUSS INDUSTRIAL ZINC PHOSPHATE PRIMER PLUSS INDUSTRIAL FINISH

* Based on recommended thickness; will vary considerably with surface characteristics, application techniques, weather and wastage.

The corresponding Safety Data Sheet (SDS) for this product shall be provided upon request. Further inquiry and SDS request can be made to transpaint@yungkong.com	
Manufactured by: Trans Paint Coatings Sdn Bhd . Lot 1393, Jalan Meranti, Bintawa Industrial Estate, 93450 Kuching, Sarawak, Malaysia. Tel: +6082 334 222 Fax: +6082 339 189 Website: www.transpaint.yungkong.com	
Disclaimer: While every care has been taken to ensure the accuracy of the information contained in this data sheet, it is provided in good faith and that no liability can be accepted arising from its use. Where the conditions of use warrant it, it is recommended that the data are checked to ensure their suitability for the use envisaged.	
Revision: 11 SEP 2023	<end of document>



INDUSTRIAL & PROTECTIVE COATINGS

www.transpaint.yungkong.com





PLUS ROAD LINE PAINT



White



Black



Yellow

PLUS INDUSTRIAL COATING



Zinc Phosphate Primer



BRI. White 71



TRU. Black 72



Rhi. Grey 73



TEL. Blue 74



DIG. Yellow 75



PET. Green 76



IND. Orange 78



TOP SERIES

TOP TRACTOR YELLOW

Top Tractor Yellow



TOP ROAD LINE PAINT



White



Black




Yellow

TOP ECONOMY METAL PRIMER/FINISH



TOP Aluminium 250



TOP Greygreen Oxide 437



TOP Red Oxide 308



TOP Black Oxide 144



TRANS PAINT COATINGS SDN BHD

Lot 1393, Jalan Meranti, Bintawa Industrial Estate 93450 Kuching, Sarawak, Malaysia.

